

AGGREGATE

GRAVEL 15-25MM

Manufacturer: Ain Touta cement company
 Production site: Aggregates and crushed sand unit
 Petrography: Limestone
 Elaboration: Crushing + screening

Particular Regulations

Specified values on which the committed producers

Granular class

Standard

Category

15	25
----	----

Standard XP P 18-545 Article 10-EN 12620 and EN

Gr _A

	8	16	25	40	50	FI	LA
Scope e		15	15				
V.S.S+U		27.5	106.5				
V.S.S.	5	20	99			20	15
V.S.I.		0	90	98	100		
V.S.I-U			82.5				

Informative part

Production results

	8	16	25	31.5	50	FI	LA
Maximum	0	8.6	98.86	100	100	7.17	29.73
Xf+1.25*ET	0	7.71	98.62	100	100	7.26	30.28
Mean Xf	0	4.58	96.16	100	100	6.76	27.58
Xf-1.25*ET0	0	1.46	93.69	100	100	6.26	24.88
Minimum	0	1.74	39.47	100	100	6.36	25.42
Ecart-types (ET)	0	2.50	1.97	0	0	0.40	2.16
Number of results	7	7	7	7	2	2	2

Chlorides = 0.28
 Sulfates = 0.35
 Carbonate = 98.0
 NF EN 1744

