

AGGREGATE

# GRAVEL BALLAST 25-50MM

Manufacturer: Ain Touta cement company  
 Production site: Aggregates and crushed sand unit  
 Petrography: Limestone  
 Elaboration: Crushing + screening

**Particular Regulations**

*Specified values on which the committed producers*

<b>Granular class</b>	<b>Standard</b>	<b>Category</b>
25    50	Standard XP P 18-545 Article 10-EN 12620 and EN	Gr <sub>A</sub>

	12.5	25	40	50	70	100	FI	LA
Scope e		15		15				
V.S.S+U		27.5		106.5				
V.S.S.	5	20		99			20	15
V.S.I.		0		80	98	100		
V.S.I-U				72.5				

**Informative part**

*Production results*

	25	40	50	70	100	FI
Maximum	16.83	96.05	100	100	100	9.10
Xf+1.25*ET	12.31	98.34	100	100	100	9.10
Mean Xf	11.26	81.82	100	100	100	9.10
Xf-1.25*ET0	10.21	65.3	100	100	100	9.10
Minimum	0.84	60.2	100	100	100	9.10
Ecart-types (ET)	6.16	13.22	0	0	0	0
Number of results	4	4	4	4	4	1

Chlorides = 0.28  
 Sulfates = 0.35  
 Carbonate = 98.0  
 NF EN 1744

