

AGGREGATE

GRAVEL 4-8MM

Manufacturer: Ain Touta cement company
 Production site: Aggregates and crushed sand unit
 Petrography: Limestone
 Elaboration: Crushing + screening

Particular Regulations

Specified values on which the committed producers

Granular class

Standard

Category

4	8
---	---

Standard XP P I8-545 Article 10-EN 12620 and EN

Gr _A

	2	4	5.63	8	11.2	16	FI	MDE
Scope e		15		15				
V.S.S+U		27.5		106.5				
V.S.S.	5	20		99			20	15
V.S.I.				80	98	100		
V.S.I-U				72.5				

Informative part

Production results

	2	4	6.3	8	11.2	16	LA	MDE
Maximum	0	27.26	90.34	98.25	100	100	8.98	11.28
Xf+1.25*ET	00	16.95	78.29	96.02	100	100	8.98	11.28
Mean Xf	0	6.14	55.67	88.76	100	100	8.40	11.28
Xf-1.25*ET0	0	4.67	33.04	81.5	100	100	7.81	11.28
Minimum	0	0	30.03	81.37	100	100	7.92	11.28
Ecart-types (ET)	0	8.65	18.1	5.81	0	0	0	0
Number of results	7	7	7	7	7	7	2	1

Chlorides = 0.28
 Sulfates = 0.27
 Carbonate = 98.0
 NF EN 1744

