

AGGREGATE

GRAVEL 8-15MM

Manufacturer: Ain Touta cement company
 Production site: Aggregates and crushed sand unit
 Petrography: Limestone
 Elaboration: Crushing + screening

Particular Regulations

Specified values on which the committed producers

Granular class

Standard

Category

8	15
---	----

Standard XP P 18-545 Article 10-EN 12620 and EN

Gr _A

	4	8	11.2	16	22.4	31.5	FI	MDE	LA
Scope e		15	30						
V.S.S+U		27.5	95						
V.S.S.	5	20	70	99			20	15	15
V.S.I.		0	25	80	98	100			
V.S.I-U		0	10						

Informative part

Production results

	4	8	16	22.4	31.5	FI	MDE	LA
Maximum	0	1.23	99.67	100	100	7.92	15.88	31.10
Xf+1.25*ET	0	0.97	102.2	100	100	7.96	17.05	31.28
Mean Xf	0	0.42	97.01	100	100	7.93	11.14	30.32
Xf-1.25*ET0	0	0.13	91.78	100	100	7.49	5.23	29.35
Minimum	0	0	97.39	100	100	7.54	6.4	29.55
Ecart-types (ET)	0	0.44	4.19	0	0	0.19	4.73	0.77
Number of results	7	7	7	7	2	2	2	2

Chlorides = 0.46
 Sulfates = 0.19
 Carbonate = 98.8
 NF EN 1744

